

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US04/043915

International filing date: 29 December 2004 (29.12.2004)

Document type: Certified copy of priority document

Document details: Country/Office: US
Number: 60/557,481
Filing date: 30 March 2004 (30.03.2004)

Date of receipt at the International Bureau: 03 February 2005 (03.02.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

1275302

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

January 19, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/557,481

FILING DATE: *March 30, 2004*

RELATED PCT APPLICATION NUMBER: *PCT/US04/43915*



Certified by

Under Secretary of Commerce
for Intellectual Property
and Director of the United States
Patent and Trademark Office

14280 U.S. PTO
033004

PTO/SB/16 (10-01)
Approved for use through 10/31/2002. OMB 0651-0032
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No. EV 436783107 US

22859 U.S. PTO
60/557481

033004

| INVENTOR(S) | | | | | |
|--|------------------------|--|---|---|--------------|
| Given Name (first and middle [if any]) | Family Name or Surname | | Residence (City and either State or Foreign Country) | | |
| Donald E. | Scott | | Taupo, New Zealand | | |
| <input type="checkbox"/> Additional inventors are being named on the _____ separately numbered sheets attached hereto | | | | | |
| TITLE OF THE INVENTION (500 characters max) | | | | | |
| DIMENSIONALLY STABLE FABRIC | | | | | |
| Direct all correspondence to: CORRESPONDENCE ADDRESS | | | | | |
| <input checked="" type="checkbox"/> Customer Number | | <div style="border: 1px solid black; padding: 2px; display: inline-block;">23618</div> | | <div style="border: 1px solid black; padding: 2px; display: inline-block;">Place Customer Number Bar Code Label here</div> | |
| OR Type Customer Number here | | | | | |
| <input checked="" type="checkbox"/> Firm or Individual Name | | Chase Law Firm, L.C. | | | |
| Address | | 4400 College Boulevard, Suite 130 | | | |
| Address | | | | | |
| City | Overland Park | State | Kansas | ZIP | 66211 |
| Country | USA | Telephone | (913) 339-9666 | Fax | 913-339-6061 |
| ENCLOSED APPLICATION PARTS (check all that apply) | | | | | |
| <input checked="" type="checkbox"/> Specification Number of Pages | | <div style="border: 1px solid black; padding: 2px; display: inline-block;">17</div> | | <input type="checkbox"/> CD(s), Number | |
| <input checked="" type="checkbox"/> Drawing(s) Number of Sheets | | <div style="border: 1px solid black; padding: 2px; display: inline-block;"></div> | | <input type="checkbox"/> Other (specify) | |
| <input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76 | | <div style="border: 1px solid black; padding: 2px; display: inline-block;"></div> | | | |
| METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT | | | | | |
| <input checked="" type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. | | | | <div style="text-align: center;">FILING FEE AMOUNT (\$)</div> <div style="border: 1px solid black; padding: 10px; width: 80px; margin: 0 auto;">80.00</div> | |
| <input checked="" type="checkbox"/> A check or money order is enclosed to cover the filing fees | | | | | |
| <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number: | | | | | |
| <div style="border: 1px solid black; padding: 2px; display: inline-block;">03-1425</div> | | | | | |
| <input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached. | | | | | |
| The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government. | | | | | |
| <input checked="" type="checkbox"/> No. | | | | | |
| <input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____ | | | | | |

Respectfully submitted,

SIGNATURE

TYPED or PRINTED NAME Sean T. Bradley

TELEPHONE (913) 339-9666

Date 3/30/04

REGISTRATION NO.
(if appropriate)
Docket Number:

46,572

3350

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C. 20231.

14230 U.S. PTO
033004

PTO/SB/17 (10-03)

Approved for use through 07/31/2006. OMB 0651-0032
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

FEE TRANSMITTAL for FY 2004

Effective 10/01/2003. Patent fees are subject to annual revision.

☒ Applicant claims small entity status. See 37 CFR 1.27

TOTAL AMOUNT OF PAYMENT (\$ 80.00

Complete if Known

| | |
|----------------------|-----------------|
| Application Number | |
| Filing Date | |
| First Named Inventor | DONALD E. SCOTT |
| Examiner Name | |
| Art Unit | |
| Attorney Docket No. | 3350 |

METHOD OF PAYMENT (check all that apply)☒ Check ☐ Credit card ☐ Money Order ☐ Other ☐ None☒ Deposit Account:Deposit Account Number
03-1425Deposit Account Name
Chase & Yakimo

The Director is authorized to: (check all that apply)

☐ Charge fee(s) indicated below ☒ Credit any overpayments☒ Charge any additional fee(s) or any underpayment of fee(s)☐ Charge fee(s) indicated below, except for the filing fee to the above-identified deposit account.**FEE CALCULATION****1. BASIC FILING FEE**

| Large Entity | | Small Entity | | Fee Description | Fee Paid |
|--------------|----------|--------------|----------|------------------------|-----------|
| Fee Code | Fee (\$) | Fee Code | Fee (\$) | | |
| 1001 | 770 | 2001 | 385 | Utility filing fee | |
| 1002 | 340 | 2002 | 170 | Design filing fee | |
| 1003 | 530 | 2003 | 265 | Plant filing fee | |
| 1004 | 770 | 2004 | 385 | Reissue filing fee | |
| 1005 | 160 | 2005 | 80 | Provisional filing fee | 80.00 |
| SUBTOTAL (1) | | | | | (\$ 80.00 |

2. EXTRA CLAIM FEES FOR UTILITY AND REISSUE

| | | | | | | | |
|--------------------|--|--------------|--|----------------|--|----------|--|
| Total Claims | | Extra Claims | | Fee from below | | Fee Paid | |
| Independent Claims | | -20** = | | X | | | |
| Multiple Dependent | | -3** = | | X | | | |

| Large Entity | | Small Entity | | Fee Description | Fee Paid |
|--------------|----------|--------------|----------|--|----------|
| Fee Code | Fee (\$) | Fee Code | Fee (\$) | | |
| 1202 | 18 | 2202 | 9 | Claims in excess of 20 | |
| 1201 | 86 | 2201 | 43 | Independent claims in excess of 3 | |
| 1203 | 290 | 2203 | 145 | Multiple dependent claim, if not paid | |
| 1204 | 86 | 2204 | 43 | ** Reissue independent claims over original patent | |
| 1205 | 18 | 2205 | 9 | ** Reissue claims in excess of 20 and over original patent | |
| SUBTOTAL (2) | | | | | (\$)-0- |

**or number previously paid, if greater; For Reissues, see above

FEE CALCULATION (continued)**3. ADDITIONAL FEES**

Large Entity Small Entity

| Fee Code | Fee (\$) | Fee Code | Fee (\$) | Fee Description | Fee Paid |
|----------|----------|----------|----------|--|----------|
| 1051 | 130 | 2051 | 65 | Surcharge - late filing fee or oath | |
| 1052 | 50 | 2052 | 25 | Surcharge - late provisional filing fee or cover sheet | |
| 1053 | 130 | 1053 | 130 | Non-English specification | |
| 1812 | 2,520 | 1812 | 2,520 | For filing a request for <i>ex parte</i> reexamination | |
| 1804 | 920* | 1804 | 920* | Requesting publication of SIR prior to Examiner action | |
| 1805 | 1,840* | 1805 | 1,840* | Requesting publication of SIR after Examiner action | |
| 1251 | 110 | 2251 | 55 | Extension for reply within first month | |
| 1252 | 420 | 2252 | 210 | Extension for reply within second month | |
| 1253 | 950 | 2253 | 475 | Extension for reply within third month | |
| 1254 | 1,480 | 2254 | 740 | Extension for reply within fourth month | |
| 1255 | 2,010 | 2255 | 1,005 | Extension for reply within fifth month | |
| 1401 | 330 | 2401 | 165 | Notice of Appeal | |
| 1402 | 330 | 2402 | 165 | Filing a brief in support of an appeal | |
| 1403 | 290 | 2403 | 145 | Request for oral hearing | |
| 1451 | 1,510 | 1451 | 1,510 | Petition to institute a public use proceeding | |
| 1452 | 110 | 2452 | 55 | Petition to revive - unavoidable | |
| 1453 | 1,330 | 2453 | 665 | Petition to revive - unintentional | |
| 1501 | 1,330 | 2501 | 665 | Utility issue fee (or reissue) | |
| 1502 | 480 | 2502 | 240 | Design issue fee | |
| 1503 | 640 | 2503 | 320 | Plant issue fee | |
| 1460 | 130 | 1460 | 130 | Petitions to the Commissioner | |
| 1807 | 50 | 1807 | 50 | Processing fee under 37 CFR 1.17(q) | |
| 1806 | 180 | 1806 | 180 | Submission of Information Disclosure Stmt | |
| 8021 | 40 | 8021 | 40 | Recording each patent assignment per property (times number of properties) | |
| 1809 | 770 | 2809 | 385 | Filing a submission after final rejection (37 CFR 1.129(a)) | |
| 1810 | 770 | 2810 | 385 | For each additional invention to be examined (37 CFR 1.129(b)) | |
| 1801 | 770 | 2801 | 385 | Request for Continued Examination (RCE) | |
| 1802 | 900 | 1802 | 900 | Request for expedited examination of a design application | |

Other fee (specify)

*Reduced by Basic Filing Fee Paid

SUBTOTAL (3) (\$)-0-

SUBMITTED BY

(Complete if applicable)

| | | | | | |
|-------------------|---|-----------------------------------|----------|-----------|--------------|
| Name (Print/Type) | Sean T. Bradley | Registration No. (Attorney/Agent) | 46,572 | Telephone | 913-339-9666 |
| Signature |  | Date | 03/30/04 | | |

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

This collection of information is required by 37 CFR 1.17 and 1.27. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 12 minutes to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

DIMENSIONALLY STABLE FABRIC

FIELD OF THE INVENTION

This invention relates to wool-synthetic blend fabrics and more particularly to flame-resistant, dimensionally stable wool-synthetic blend fabrics suitable for use in
5 aircraft and other transport interiors.

BACKGROUND OF THE INVENTION

Upholstery fabrics made from wool are known to have an attractive appearance and feel to the touch. Due to the tendency of wool to shrink after washing in water, however, attempts have been made to substitute wool fabrics with fabrics made from
10 synthetic materials such as polyester. The appearance and feel of fabrics made from synthetic materials, however, has been found to be inferior to that of fabrics made from wool. Fabrics made from blends of wool fibers with certain synthetic fibers retain some of the aesthetic features of wool as well as some of the cost benefits and potential property advantages of synthetics.

15 In the aircraft industry, seat cover fabrics are subject to specifications provided by aircraft manufacturers such as Airbus and Boeing. The relevant Airbus technical specification, for example, is TL 25/5092/83. The relevant flammability, smoke and toxicity portions of the standard are FAR 25.853 (b), appendix F, amended 32, JAR 25853 (b), appendix change 10, and ABD 0031 (previously numbered ATS 1000.001). These
20 specifications include standards for abrasion resistance including resistance to abrasion simulated by a Martindale tester. Resistance to stains resulting from spills, and to loss of color and shrinkage due to washing, is also specified. Seat cover fabrics may be required to meet specifications after a minimum of 10 washings. An areal weight below 470 g/m² is
(Docket 3350)

specified. It is desirable that shrinkage during service life, including shrinkage due to cleaning processes, be minimized. Resistance to pilling, corrosion and color loss may also be specified.

5 The relevant Boeing specification is BMS 8-236, for general upholstery interior applications. The flammability standard is provided by BSS7230, a twelve second vertical burn test, in which the sample is required to self extinguish within fifteen seconds, with a burn length of less than eight inches. Drips, if any, are required to extinguish in less than five seconds. Smoke emissions of less than 200 are specified according to BSS7238. Prescribed limits for individual toxic components in toxic gas emissions are tested according to BSS 7239. Dimensional stability is evaluated after prescribed cleaning, whether dry
10 cleaning or water washing methods are used. While zero shrinkage is ideal, shrinkage levels of less than 6%, in both warp and fill directions, are acceptable. Standards for appearance, snag resistance, pilling resistance, color fastness and strength are part of the overall specification.

15 Wool fabrics are typically cleaned using a dry-cleaning process, including immersion in a solvent such as perchloroethylene, in order to maintain the dimensional stability of the fabric. Due to environmental and cost considerations, it would be desirable to clean wool-based fabrics without the use of perchloroethylene or other organic solvents. Water containing surfactants or detergents is highly effective in cleaning such fabrics,
20 however, use of water-based cleaning solutions has been limited by the tendency of wool based fabrics to shrink after being subjected to such solutions. Synthetic fibers, on the other hand, are typically highly resistant to shrinkage following washing in water. Synthetic fibers, however, tend to be highly flammable.

Because of the nature of the constituent parts of the above mentioned wool-synthetic blends, such blends in the prior art are typically neither flame resistant, nor shrink resistant when washed in water. There is a need for fabrics made from wool-synthetic blends that will meet the special requirements for aircraft interiors.

5

BRIEF DESCRIPTION OF THE INVENTION

In one embodiment of the invention, a method of producing a dimensionally stable, fire-resistant fabric suitable for use on aircraft includes the steps of providing a yarn having a blend of wool fibers and fire-resistant synthetic fibers, the wool
10 fibers comprising approximately 30% to 70% of the blend, weaving the yarn to form a fabric, and dimensionally stabilizing the fabric to achieve a washable woven structure resistant to shrinkage. The synthetic fibers may include polyester fibers produced or treated to enhance fire resistance. The fabric may be dimensionally stabilized by heat setting or by applying a coating such as neoprene or polyurethane.

15 In another embodiment a method is provided for producing a dimensionally stable, fire-resistant fabric by spinning wool and fire-resistant polyester fibers to form a yarn, weaving the yarn to form a fabric, and heat-setting the fabric to produce a finished material that passes Airbus and/or Boeing specifications.

In a further embodiment a method is provided for producing a fire-resistant
20 wool-based yarn by spinning shortened wool fibers with fire-resistant polyester fibers in a vortex spinning apparatus. The yarn is woven into a fabric that passes aircraft manufacturer specifications. The fabric is stabilized dimensionally, to prevent or substantially reduce shrinkage during use, by heat-setting the fabric in a stenter apparatus or by applying a coating

such as neoprene or polyurethane. In one embodiment, the fabric is dimensionally stabilized such that it resists shrinkage after water washing. In a further embodiment, the method includes treating the yarn or fabric with zirconium to augment the fire-resistant properties.

In yet another embodiment a method is provided for producing a

5 dimensionally stable fabric by providing wool fibers, an effective percentage thereof cut or broken to fall within a selected length range, providing fire-resistant synthetic fibers, spinning the wool and synthetic fibers to produce a wool-synthetic blend yarn, wherein the wool fibers comprise approximately 30% to 70% of the blend, weaving the yarn to form a fabric, and providing dimensional stabilization by application of a polymer coating or by heat setting the

10 fabric to produce a final product that passes aircraft manufacturer specifications.

Wool fibers having a typical length of no greater than approximately five centimeters may be prepared by stretch-breaking. The synthetic fibers may include polyester fibers. Fibers may be spun by delivering the fibers to a ring spinning, air-jet spinning or vortex spinning apparatus for spinning the fibers into a yarn. The fabric may be heat-set by

15 securing and heating the fabric within a stenter. When passing the fabric through a stenter, sufficient heat is applied to set the fabric and produce a dimensionally stabilized fabric resistant to shrinkage. Further steps may include applying zirconium fire retardant to the fabric and applying a coating to bind the zirconium fire retardant to the fabric.

DETAILED DESCRIPTION

In one embodiment, wool fibers are first prepared by reducing their length. Wool tops, consisting of fibers that are approximately 5.5 to 8 cm in length, are passed through a stretch-breaking machine to reduce their lengths to approximately 2 to 5 cm. It is advantageous if the fibers are approximately 3 to 4 cm in length. It is advantageous if the wool fibers have diameters in the range of 13 to 25 microns, and particularly advantageous if the wool fibers have diameters in the range of approximately 22 to 25 microns.

After stretch breaking, the wool fibers are combined with flame retardant (FR) synthetic fibers (such as polyester) having a length of approximately 2 to 5 cm, and the resulting combined fiber bundles are passed through one or more draw frames. The drafted wool and FR fiber bundles are introduced into a spinning machine at such relative rates as to achieve wool contents in the range of approximately 30 to 70 percent. It is advantageous to the properties of the resulting fabric if the wool content is in the range of approximately 40 to 60 percent.

15 Spinning Technology

Typically, carding occurs prior to, or as an initial step in, the spinning process. Through carding, fibers are straightened and made relatively parallel to one another. After carding the fibers form a thin layer called a web. The web is gathered into a loose rope called a sliver. The sliver is typically wound into a large can and then moved to a draw frame. In the drawing process, multiple cans of sliver are drawn together to form a combined sliver.

Ring spinning is a relatively slow spinning technology that typically yields a high quality yarn. During ring spinning, sliver is fed into the drafting zone of the ring spinning frame. The drafting zone has one roller that turns relatively slow and feeds the

sliver and another roller that turns relatively fast. The faster roller pulls out a few fibers at a time forming a fine stream of fibers that are fed to a rotating spindle inside a ring. As the spindle rotates, it drags a slower moving traveler on the ring. The ring twists the fibers as they are wound onto a bobbin that rides on the spindle. After spinning, the yarn may then be
5 used for weaving, perhaps after being further transferred to other holding structures. Ring spinning has been the preferred method of producing high quality wool yarns that demonstrate superior feel to the touch and abrasion resistance.

The air-jet spinning method uses air currents to twist fibers together, resulting in higher throughput and productivity than ring spinning. Air-jet spinning may be
10 used to spin blends of wool and synthetic FR fibers, but yields yarns with reduced abrasion resistance in comparison with ring and vortex spinning.

The air vortex spinning method is a particularly efficient spinning method that is capable of spinning yarns at very high speeds and that yields a yarn having a relatively smooth texture and increased abrasion resistance. A vortex spinning apparatus
15 typically takes drawn sliver and drafts it to the desired yarn count via a four-roller drafting unit. The drafted fibers are then sucked into a nozzle where a high speed air vortex wraps the fibers around the outside of a hollow stationary spindle. Yarn twist is then imparted as the fibers are pulled down a shaft that runs through the middle of the spindle.

An example of a vortex spinning apparatus is described in the patent to
20 Mori, patent No. 6,370,858, hereby incorporated by reference. Mori discloses a vortex spinning method in which a drafted fiber bundle is supplied to a nozzle block and then to a hollow guide shaft. A core fiber is also fed to the nozzle block and then to the hollow guide shaft. Vortex air currents ejected from spinning nozzles in the nozzle block cause inversely turned fibers to wrap the fiber bundle and core fiber to create core yarn. The core fiber may

be multi-filament in which case the vortex air currents balloon the multiple filaments, resulting in the filaments being partially separated from one another. The vortex air currents insert the front ends of the fibers into the clearances between the separated filaments, and cause the other ends of the fibers to wrap around the multi-filament core fiber, resulting in the
5 creation of the core yarn.

In another embodiment, the fiber bundle, comprising a blend of shortened wool and synthetic fibers, is delivered to the vortex spinner and spun without use of core fiber. In this embodiment, vortex nozzle apertures and build pressures are optimized for spinning such that a percentage of the fibers delivered to the spinner tend to form a core.
10 Remaining fibers are simultaneously spun or wrapped around this core thereby causing the core of the yarn to build as the yarn strand itself is formed.

The spinning speed of a vortex spinner is much faster than that provided by ring spinning with the ring method typically producing yarn at the rate of 20 meters per minute and the vortex method typically producing yarn at the rate of 400 meters per minute.
15 The vortex method does not readily accommodate the longer fibers typically used in wool spinning, however, and it has been found to be advantageous to reduce the fiber lengths as illustrated in the various embodiments of the invention disclosed herein.

Preparation of the Fabric

In the various embodiments contained herein, the spinning process used to
20 produce the yarn may include ring spinning, air-jet spinning, air vortex spinning or other appropriate means. It is advantageous, however, to spin the yarn using a vortex spinning method and apparatus.

After spinning, the yarn is typically dyed to a selected color and then woven into a fabric. The particular weave is typically determined by the requirements of the

eventual use of the fabric. Appropriate weaves include those known for use by American Airlines and United Airlines.

After weaving, the fabric is heat-set to increase dimensional stability of the fabric. It is advantageous if the heat setting includes the step of affixing the fabric within a stenter frame so that a given dimension may be controlled during the heat-setting process.

The fabric is heat set within the stenter by heating the fabric to a temperature in excess of 100°C. The actual temperature used is primarily dependent upon the chemical nature of the synthetic fiber being used. Multiple heating bays may be used, each successive bay typically providing increased heat. In the case where a polyester fiber is used, the maximum

temperature is typically set between approximately 170°C and 220°C. Dwell time, the time period in which heat is applied to the fabric in the stenter may be adjusted according to temperatures used and composition of the fabric. The fabric is typically heated by provision of dry heat using appropriate means such as a gas fired burner and heat exchanger. In one embodiment, dimensional stability results from incipient melting of polyester (or other synthetic) fibers and subsequent bonding of the fibers to form a continuous or semi-continuous polyester network or lattice within the fabric.

In an embodiment directed to vortex spun yarn, wool tops are passed through a stretch-breaking apparatus and the fiber length is thereby reduced to approximately 3 to 4 cm. The wool fibers are then combined with synthetic FR staple (such as polyester) having an approximate length of 3 cm, at a ratio of one part wool fiber to one part synthetic FR fiber, to form an intimate blend. The combined fibers ("intimate blend") are drafted on a drawframe and then spun in a vortex spinner.

Portions of the yarn are dyed to a desired color or colors and then woven into a fabric suitable for use in aircraft such as for seat upholstery. The fabric is heat set in a

stenter at an appropriate temperature (approximately 190°C if the synthetic primarily comprises polyester) for approximately 30 seconds. As a result of this process the fabric meets airline interior fabric test specifications, including those for fire resistance, abrasion and shrinkage after water washing. By way of example, a fabric may be produced in accordance with the above embodiment to pass Airbus specification TL 25/5092/83 and Boeing specification BMS 8-236. Fabric meeting these specifications may be produced without heat setting if the fabric is to be dry-cleaned rather than subjected to water washing.

Representative passing test results include the following for flame resistance, abrasion resistance and relaxation and felting shrinkage (dimensional stability).

Table 1. Flame Resistance
(Federal Aviation Regulation § 25.853(a))

| Specimen | Average Burn Time After Flame (seconds) | Average Burn Length (mm) | Average Dripping Flame Time (seconds) |
|----------|---|--------------------------|---------------------------------------|
| Warp | 8.7 | 83 | Nil |
| Weft | 7.3 | 77 | Nil |

Table 2. Abrasion Resistance
(Martindale Method)

| Total Loading | Average No. Cycles to Mechanical End Point | No. Cycles to Grey Scale 3 Color Change End Point | No. Cycles to Unacceptable Appearance Change End Point |
|---------------|--|---|--|
| 12Kpa | 46,500 | Not reached | Not reached |

Table 3. Dimensional Stability
(Wool/Polyester, American Airlines Weave, No. of Cycles: 7A x 1, 5A x 2)

| | Width | Length |
|------------------------|-------|--------|
| % Relaxation shrinkage | -2.1 | -3.5 |
| % Felting shrinkage | -1.5 | -2.1 |
| % Total shrinkage | -3.6 | -5.5 |
| % Area shrinkage | -3.6 | |

As an alternative to fabric produced from a blend of wool and synthetic FR fiber, yarn may be spun from a blend of wool and non-fire resistant synthetic fiber or from wool alone. Fabric woven from such yarn may then be treated with zirconium fire retardant. Such treatment typically includes a coating to bind the zirconium fire retardant to the fabric.

5 If woven from yarn spun from wool and without the addition of synthetic fibers, fabric would typically not be heat set but would retain dimensional stability during use through dry-cleaning rather than washing with water.

Additionally, yarn spun from a blend of wool and synthetic fibers, the wool fibers comprising between approximately 30 to 70 percent of the blend, may be treated with zirconium-based fire retardants prior to weaving to augment the fire-resistant qualities of the resulting fabric. Zirconium treatment may be applied to any of the fabrics set forth above to enhance fire-resistance.

10

To resist dislodging of the zirconium fire retardant from the fabric during washing, the fabric may be treated with polyurethane or other appropriate material to coat the zirconium and bind it to the fabric.

15

It is to be understood that while certain forms of this invention have been illustrated and described, it is not limited thereto except insofar as such limitations are included in the following claims and allowable equivalents thereof.

CLAIMS

Having thus described the invention, what is claimed as new and desired to be secured by Letters Patent is as follows:

1. A method of producing a dimensionally stable fabric, said method
5 comprising the steps of:
 providing a yarn having a blend of wool fibers and fire-resistant synthetic fibers, the wool
 fibers comprising approximately 30% to 70% of the blend,
 weaving the yarn to form a fabric, and
 stabilizing the fabric dimensions to create a woven structure resistant to shrinkage.
- 10 2. The method of claim 1, wherein the step of providing yarn includes
 providing synthetic fibers that comprise polyester fibers.
3. The method of claim 1, wherein the step of providing yarn includes
 providing wool fibers having diameters of approximately 13 to 25 microns.
4. The method of claim 1, wherein the step of providing yarn includes
15 providing wool fibers having diameters of approximately 22 to 25 microns.
5. The method of claim 1, wherein the step of stabilizing comprises heat
 setting the fabric.
6. The method of claim 5, wherein the step of stabilizing includes the steps
 of securing the fabric within a stenter and heating the fabric to a temperature within the range
20 of 170 to 220°F for approximately 30 seconds.

7. The method of claim 1, wherein the step of stabilizing comprises applying a coating to the fabric.

8. The method of claim 7, wherein the step of stabilizing comprises applying a synthetic polymer coating to the fabric.

5 9. The method of claim 8, wherein said polymer comprises neoprene.

10. The method of claim 8, wherein said polymer comprises polyurethane.

11. A method of producing a dimensionally stable fabric, said method comprising the steps of:

providing wool fibers, an effective percentage thereof within a selected length range,

10 providing fire-resistant synthetic fibers,

spinning said fibers to produce a wool-synthetic blend yarn, the wool fibers comprising

approximately 30% to 70% of the blend,

weaving the yarn to form a fabric, and

heat setting the fabric to produce a fabric that passes aircraft manufacturer specifications.

15 12. The method of claim 11, wherein the fabric is produced to pass Airbus specification TL 25/5092/83.

13. The method of claim 11, wherein the fabric is produced to pass Boeing specification BMS 8-236.

14. The method of claim 11, wherein the step of spinning includes vortex
20 spinning.

15. A method of producing a dimensionally stable fabric, said method comprising the steps of:

preparing wool fibers by stretch-breaking an effective percentage thereof to a length no greater than approximately five centimeters,
5 providing fire-resistant synthetic fibers,
spinning the fibers to produce a yarn having a wool fiber to synthetic fiber ratio in the range of approximately 70:30 to 30:70,
weaving the yarn to form a fabric, and
dimensionally stabilizing the fabric.

10

16. The method of claim 15, wherein the spinning step includes delivering the fibers to a ring spinning apparatus for spinning the fibers into a yarn.

17. The method of claim 15, wherein the spinning step includes delivering the fibers to an air-jet spinning apparatus for spinning the fibers into a yarn.

15

18. The method of claim 15, wherein the spinning step includes delivering the fibers to a vortex spinning apparatus for spinning the fibers into a yarn.

19. The method of claim 15, wherein the step of dimensionally stabilizing includes applying a coating to the fabric thereby producing a dimensionally stabilized fabric resistant to shrinkage.

20

20. The method of claim 15, wherein the step of dimensionally stabilizing includes applying sufficient heat to the fabric to set the fabric thereby producing a dimensionally stabilized fabric resistant to shrinkage.

21. The method of claim 20, wherein the step of applying sufficient heat includes the steps of securing and heating the fabric within a stenter.

22. The method of claim 15, further including the step of applying zirconium fire retardant to the fabric.

5 23. The method of claim 15, further including the step of applying a coating to bind the zirconium fire retardant to the fabric.

24. A method of producing a dimensionally stable fabric, said method comprising the steps of:

preparing wool fibers by stretch-breaking an effective percentage thereof to a length no greater than approximately five centimeters,

5 providing fire-resistant synthetic fibers, an effective percentage thereof having a length no greater than approximately five centimeters,

vortex spinning the fibers to produce a yarn having a wool fiber to synthetic fiber ratio in the range of approximately 70:30 to 30:70, and

weaving the yarn to form a fabric.

10 25. The method of claim 24, wherein the fabric is produced to pass Airbus specification TL 25/5092/83.

26. The method of claim 24, wherein the fabric is produced to pass Boeing specification BMS 8-236.

15 27. The method of claim 24, further including the step of passing the fabric through a stenter, wherein sufficient heat is applied to set the fabric and produce a dimensionally stabilized fabric resistant to shrinkage.

28. The method of claim 24, further including the step of dimensionally stabilizing the fabric through application of a polymer coating.

20 29. The method of claim 24, further including the step of applying zirconium fire retardant to the fabric.

30. The method of claim 23, further including the step of applying a coating to bind the zirconium fire retardant to the fabric.

31. A method of producing fabric for aircraft and other transport interiors, said method comprising the steps of:

5 preparing wool fibers by stretch-breaking an effective percentage thereof to a length no greater than approximately five centimeters, vortex spinning the fibers to product a yarn, and weaving the yarn to form a fabric.

10 32. The method of claim 30, wherein the fabric is produced to pass Airbus specification TL 25/5092/83.

33. The method of claim 30, wherein the fabric is produced to pass Boeing specification BMS 8-236.

34. The method of claim 30, wherein the fabric produced is suitable for dry-cleaning.

15 35. The method of claim 30, further including the step of applying zirconium fire retardant to the fabric.

36. The method of claim 30, further including the step of applying a coating to bind the zirconium fire retardant to the fabric.

ABSTRACT OF THE DISCLOSURE

A method of producing a dimensionally stable, fire-resistant fabric including the steps of spinning yarn from wool and fire-resistant synthetic fibers, weaving the yarn to form a fabric, and dimensionally stabilizing the fabric to produce a textile that passes
5 aircraft manufacturer specifications.